

## Tork Premium Multipurpose Cloth 520 Gris Feuille à Feuille



<b>N° Article</b>	520378
<b>Système</b>	W4 Top Pak
<b>Couleur</b>	Grey
<b>Impression</b>	No
<b>Longueur non- plié</b>	42,8 cm
<b>Largeur non-plié</b>	38,5 cm
<b>Longueur pliée</b>	10,8 cm

## Caractéristiques du produit

Chiffon non-tissé multi-usages Sensation et résistance textile  
Souple et doux, nettoie toutes les surfaces, sans les rayer  
Résiste à l'eau et aux solvants

## Conditionnement

### Spécifications Unité Consommateur

Pcs/Con: 140

Poids brut/con: 1,6764 kg

Poids net/con: 1,5 kg

Emballage: Plastic

EAN Con: 7322540057522

### Spécifications Unité Transport

Emballage trp: Carton

Con/Trp: 5

Longueur, trp: 555 mm

Largeur, trp: 396 mm

Hauteur, trp: 239 mm

Volume, trp: 0,05253 m<sup>3</sup>

Poids brut, trp: 8,382 kg

Poids net /trp: 7,5 kg

Ean trp: 7322540057539

Pcs Trp: 700

Trp Palette: 36

## **Environnement**

### **Contenu**

Chemical pulp Polypropene Polyester Chemicals

### **Matériel**

#### Chemical pulp

Chemical pulp is produced either from softwood or hardwood. The wood chips are boiled together with chemicals and the major part of the lignin is removed. Chemical pulp is bleached in order to achieve a clean, bright and strong product, but also to increase the hygienic and absorbent qualities.

There are two major bleaching methods: ECF (elementary chlorine free) and TCF (totally chlorine free).

ECF is based on oxygene, chlorine dioxide and hydrogen peroxide. TCF is based on hydrogen peroxide and ozone.

ECF is used in this product.

#### Polypropene

Polypropene fibre is produced from polypropene resin. The resin is melted in an extruder and spun to fibres through spinnerettes and cooled with air. Fibres are then cut to intended fibrelength.

#### Polyester

Polyester fibre is produced from terephtalic acid and ethyleneglycol, which react through condensation to polyester resin. The molten resin is spun to fibres through spinnerettes and cooled with air. Fibres are then cut to intended fibrelength. The fibre used contains black pigments.

#### Chemicals

Both functional and process chemicals are used. The functional chemical used is wetstrength agent. The wetstrength agent is a polyamide (from polyamidine/epichlorhydrinepolymer) with a very high affinity to the fibre.

Process chemical used is a surfactant.

### **Production**

This product is produced at Suameer mill, The Netherlands, and certified according to ISO 9001:2000, ISO 14001 and EMAS.

### **Destruction**

This product is mainly used for industrial processes and hence it will be contaminated with different substances. This will determine how the used product will be destructed. The product itself is suitable for incineration. Contact local authorities before destruction.



© 2005 Tissue Europe. Tel. +33 (0)1 41 84 60 00. Email: [tork.fr@sca.com](mailto:tork.fr@sca.com).

[Statut juridique](#). Pour obtenir des informations sur Tork, visitez notre site Web à l'adresse [www.sca.com](http://www.sca.com).